




CE2035



CE2036




CE2037




CE2038



CE2039










CE2043



CE2044



Poids (en g/m²)	210
Épaisseur (en mm)	0.37
Composition	100 % Fibre de verre
Soudable	-
Entretien	Épongeable

Recto	Réf. BV	Transmission solaire	Réflexion solaire	Absorption solaire	g _{tot}	Transmission lumière visible
	CE2035	42 %	54 %	4 %	0,40	42 %
	CE2036	40 %	52 %	8 %	0,41	40 %
	CE2037	32 %	42 %	26 %	0,44	31 %
	CE2038	31 %	42 %	27 %	0,50	31 %
	CE2039	15 %	21 %	64 %	0,50	14 %
	CE2043	7 %	10 %	83 %	0,54	5 %
	CE2044	3 %	5 %	92 %	0,55	3 %