



Vénitiens Alu 50 mm Cat. 1


filtersun



0150




0204




0606




1459




1650




1858




1861




2548




3750




3790



4273




4451



4459



4756



4798



4806




7010



7326




9451




9453



9455



9456



9457



Autre
Tarif 1



Intérieur

Épaisseur (en mm)

0.22

Coeff. ouverture (en %)












0.00













Composition

Aluminium

Soudable

-

Recto	Réf.	Transmission solaire	Réflexion solaire	g _{tot}	Transmission lumière visible
	0150	0 %	69,5 %	0,34	0 %
	0204	0 %	64,7 %	0,35	0 %
	0606	0 %	57 %	0,38	0 %
	1459	0 %	10,6 %	0,53	0 %
	1650	0 %	20,7 %	0,49	0 %
	1858	0 %	5,2 %	0,54	0 %
	1861	0 %	4,8 %	0,54	0 %
	2548	0 %	53,2 %	0,39	0 %
	3750	0 %	55,6 %	0,39	0 %
	3790	0 %	52,9 %	0,40	0 %
	4273	0 %	55 %	0,38	0 %

Recto	Réf.	Transmission solaire	Réflexion solaire	gtot	Transmission lumière visible
	4451	0 %	61,9 %	0,36	0 %
	4459	0 %	68,1 %	0,34	0 %
	4756	0 %	33,4 %	0,45	0 %
	4798	0 %	7,3 %	0,54	0 %
	4806	0 %	50,2 %	0,40	0 %
	7010	0 %	47,2 %	0,41	0 %
	7326	0 %	64,8 %	0,35	0 %
	9451	0 %	68,2 %	0,35	0 %
	9453	0 %	9,9 %	0,54	0 %
	9455	0 %	12,9 %	0,53	0 %
	9456	0 %	5,7 %	0,55	0 %
	9457	0 %	73,9 %	0,33	0 %